

AMENDMENTS TO THE CLAIMS

The listing of claims will replace all prior versions and listings of claims in the application:

1. **(Currently Amended)** A glass substrate for a magnetic recording medium formed to have a disc shape and including ridge shaped textures extending along concentric circles on a main surface,

wherein the textures have a width W that is between 10 and 200 nm at a reference plane obtained by measuring a 10 μm square range with an atomic force microscope, the textures have a height H that is between 2 and 10 nm, and the textures have a ratio (R_p/R_{MS}) of a maximum mountain height with respect to a root mean square roughness that is less than or equal to 15,

wherein when the textures are cut along a plane parallel to the main surface in the 10 μm square measurement range of the atomic force microscope, the percentage of the area of the textures in of the cut plane with respect to the entire area of the measurement range is defined as a bearing ratio (BR), the height of the textures when the bearing ratio is 50% is defined as a reference height, and the height of the textures from the reference height in a plurality of bearing ratios is defined as a bearing height (BH), the difference between the bearing height (BH) when the bearing ratio (BR) is 0.01% and the bearing height (BH) when the bearing ratio (BR) is 0.4% is between 0.01 and 1.0 nm for the textures.

2. **(Original)** The glass substrate for a magnetic recording medium according to claim 1, wherein the width W at the reference plane of the textures is between 10 and 20 nm.

3. **(Previously Presented)** The glass substrate for a magnetic recording medium according to claim 1, wherein the width W at the reference plane of the textures is between 10 and 20 nm, the height H of the textures is between 2 and 5 nm, and the ratio (R_p/R_{ms}) of the maximum mountain height with respect to the root mean square roughness RMS of the textures is less than or equal to 3.

4. **(Cancelled)**

5. **(Currently Amended)** A glass substrate for a magnetic recording medium formed to have a disc shape and including ridge shaped textures extending along concentric circles on a main surface,

wherein the textures have a width W that is between 10 and 200 nm at a reference plane obtained by measuring a 10 μm square range with an atomic force microscope, the textures have a height H that is between 2 and 10 nm, and the textures have a ratio (R_p/R_{ms}) of a maximum mountain height with respect to a root mean square roughness that is less than or equal to 15,

wherein when the textures are cut along a plane parallel to the main surface in the 10 μm square measurement range of the atomic force microscope, the percentage of the area of the textures in the cut plane with respect to the entire area of the measurement range is defined as a bearing ratio (BR), the height of the textures when the bearing ratio is 50% is defined as a reference height, and the height of the textures from the reference height in a plurality of bearing ratios is defined as a bearing height (BH), the difference between the bearing height (BH) when the bearing ratio (BR) is 0.4% and the bearing height (BH) when the bearing ratio (BR) is 1.0% is between 0.15 and 0.20 nm for the textures.

6. **(Currently Amended)** A glass substrate for a magnetic recording medium formed to have a disc shape and including ridge shaped textures extending along concentric circles on a main surface,

wherein the textures have a width W that is between 10 and 200 nm at a reference plane obtained by measuring a 10 μm square range with an atomic force microscope, the textures have a height H that is between 2 and 10 nm, and the textures have a ratio (R_p/R_{rms}) of a maximum mountain height with respect to a root mean square roughness that is less than or equal to 15,

wherein when the textures are cut along a plane parallel to the main surface in the 10 μm square measurement range of the atomic force microscope, the percentage of the area of the textures in the cut plane with respect to the entire area of the measurement range is defined as a bearing ratio (BR), the height of the textures when the bearing ratio is 50% is defined as a reference height, and the height of the textures from the reference height in a plurality of bearing ratios is defined as a bearing height (BH), the difference between the bearing height (BH) when the bearing ratio (BR) is 0.01% and the bearing height (BH) when the bearing ratio (BR) is 0.4% is between 0.2 and 0.7 nm, and the difference between the bearing height (BH) when the bearing ratio (BR) is 0.4% and the bearing height (BH) when the bearing ratio (BR) is 1.0% is between 0.17 and 0.20 nm for the textures.

7. **(Currently Amended)** The glass substrate for a magnetic recording medium according to claim 1, wherein when the textures are cut along a plane parallel to the main surface in the 10 μm square measurement range of the atomic force microscope, the percentage of the area of the textures in the cut plane with respect to the entire area of the measurement range is defined as a bearing ratio (BR), the height of the textures when the bearing ratio is 50% is defined as a reference height, and the height of the textures from the reference height in a plurality of bearing ratios is defined as a bearing height (BH), the difference between the bearing height (BH) when the bearing ratio (BR) is 0.4% and the bearing height (BH) when the bearing ratio (BR) is 1.0% is less than the difference between the bearing height (BH) when the bearing ratio (BR) is 1.0% and the bearing height (BH) when the bearing ratio (BR) is 15% for the textures.

8. **(Previously Presented)** The glass substrate for a magnetic recording medium according to claim 1, wherein an average depth D of depressions of the textures in the 10 μm square measurement range of the atomic force microscope is less than or equal to 2 nm, and a ratio H/D of a height H with respect to the average depth D of the depressions of the textures is greater than or equal to 10.

9. **(Previously Presented)** The glass substrate for a magnetic recording medium according to claim 1, wherein the textures include low frequency components, obtained in the 10 μm square measurement range of the atomic force microscope, and high frequency components, obtained in a 1 μm square or 0.1 μm square measurement range of the atomic force microscope, superimposed on the low frequency components, and being finer than the low frequency components, wherein the textures of the high frequency components have a width W' that is between 0.1 and 20 nm, and the textures of the high frequency components have a height H' that is between 0.1 and 1 nm.

10. **(Original)** The glass substrate for a magnetic recording medium according to claim 9, wherein the width, W' of the textures of the high frequency components is between 1 and 5 nm, and the height H' of the textures of the high frequency components is between 0.3 and 0.8 nm.

11. **(Previously Presented)** The glass substrate for a magnetic recording medium according to claim 1, wherein the textures in the 10 μm square measurement range of the atomic force microscope has a maximum valley depth R_v of 10 nm or less.

12. **(Previously Presented)** The glass substrate for a magnetic recording medium according to claim 1, wherein the ratio (H_{v1}/H_{c2}) of a coercive force H_{c1} in a circumferential direction with respect to a coercive force H_{c2} in a radial direction is greater than 1.1 and less than or equal to 1.3.

13. **(Previously Presented)** The glass substrate for a magnetic recording medium according to claim 1, wherein the ratio (R_p/R_{ms}) of a maximum mountain height R_p with respect to a root mean square roughness RMS of the textures is less than or equal to 5.

14. **(Withdrawn)** A method for manufacturing a glass substrate for a magnetic recording medium, the method including a disc machining process for machining a sheet of glass material into a disc shape, a polishing process for polishing a main surface of the disc-shaped glass substrate with a polishing member, a washing process for washing off residual polishing agent from the main surface of the glass substrate, and a texture formation process for forming textures on the main surface of the washed glass substrate, wherein an arithmetic mean roughness R_a of the main surface of the washed glass substrate indicates a value of between 0.35 and 1.0 nm when a 10 μm square range is measured with the atomic force microscope.

15. **(Withdrawn)** The method for manufacturing the glass substrate for a magnetic recording medium according to claim 14, wherein a chemical strengthening process for chemically strengthening the glass substrate is included before the texture formation process.

16. **(New)** The glass substrate for a magnetic recording medium according to claim 1, wherein the difference between the bearing height when the bearing ratio is 0.4% and 1.0% is between 0.15 nm and 0.18 nm.

17. **(New)** The glass substrate for a magnetic recording medium according to claim 1, wherein the difference between the bearing height when the bearing ratio is 0.01% and 0.4% is between 0.18 nm and 0.45 nm.

18. **(New)** The glass substrate for a magnetic recording medium according to claim 5, wherein at least one of the difference between the bearing height when the bearing ratio is 0.4% and 1.0% is between 0.15 nm and 0.18 nm and the difference between the bearing height when the bearing ratio is 0.01% and 0.4% is between 0.18 nm and 0.45 nm.

19. **(New)** The glass substrate for a magnetic recording medium according to claim 6, wherein at least one of the difference between the bearing height when the bearing ratio is 0.4% and 1.0% is between 0.15 nm and 0.18 nm and the difference between the bearing height when the bearing ratio is 0.01% and 0.4% is between 0.18 nm and 0.45 nm.

20. **(New)** The glass substrate for a magnetic recording medium according to claim 5, wherein the ratio (H_v1/H_c2) of a coercive force H_c1 in a circumferential direction with respect to a coercive force H_c2 in a radial direction is greater than 1.1 and less than or equal to 1.3.

21. **(New)** The glass substrate for a magnetic recording medium according to claim 6, wherein the ratio (H_{v1}/H_{c2}) of a coercive force H_{c1} in a circumferential direction with respect to a coercive force H_{c2} in a radial direction is greater than 1.1 and less than or equal to 1.3.